Intuition 4856

Intuition 4856





Honey

1716

Sage

1721

Hickory

1715

Coral 1714



Ochre 1718



Scarlet 1720



Viridian 1723



Peacock 1722



Admiral 1724



Bisque



Platinum 1717



Slate 1719



Charcoal 1712

Specifications

Content	55% post-consumer recycled polyester 34% pre-consumer recycled polyester 11% polyester
Weight	11.2 ± 1.0 oz./lin. yd.
Width	54" min. useable
Repeat	none
Backing	acrylic backcoating
Treatment	stain repellent


Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination	
NRC of fabric in front of anechoic termination	.95

Performance

•	*	Col Gra
	Ø	Col Gra
	×	Bre 21 0
		Car

plorfastness to Light (AATCC 16.3 Option 3) ade 4 min. at 40 hours

olorfastness to Crocking (AATCC 8) ade 4 min. dry & Grade 3 min. wet

eaking Strength (ASTM D5034) 0 lbf warp and 200 lbf fill

Seam Slippage (ASTM D4034) 30 lbf warp and 45 lbf fill

Pilling Resistance (ASTM D3511) Class 4 min.



Flammability

CA Technical Bulletin 117-2013 Section 1 ASTM E84 Class I or A



Abrasion (ASTM D4157) 100,000 double rubs cotton duck

Sustainability



Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Visit guilfordofmaine.com for samples.



program. Additional testing of this U.L. recognized component fabric is not required on approved panels from participating manufacturers.